

Recipes-Steps for Surface Design with Dye

Step 1: Prepare fabric

<u>Only if necessary</u>: scour the fabric by machine washing for 15 minutes:

 Hot water
 140° F (60° C)

 Soda ash
 1/2 tsp (2.5 ml) per 1 lb (455 g) fabric

 Synthrapol SP
 1/2 tsp (2.5 ml) per 1 lb (455 g) fabric

Soak dry fabric in soda solution until it is thoroughly wet—5 to 20 minutes.

Warm Soda ash 1 gallon (3.8 liters) 9 Tbs (135 ml)

Step 2: Prepare print paste

Stir continuously while adding dry ingredients

Short Cut using prepared MIX:

Add 5 ½ TBS (80 ml) Print Paste Mix SH to one cup (240 ml) warm water.

EXTRA THICK print paste: use 1-2 TBS more prepared MIX per cup of water

OR mix from scratch adding ingredients in following order

Warm water	3 cups (720 ml)
Granular urea	6-1/2 Tbs (98 ml)
Metaphos	1-1/2 tsp (7.5 ml)
Sodium alginate SH	6 tsp (30 ml)
Water	To make a total of 1 quart (960 ml)


A CARACTERISTICS OF THE CONTRACTOR OF TO O

EXTRA THICK print paste from scratch: use 2-4 tsp additional Sodium alginate SH

Step 3: Prepare the urea water.

Use to make lighter THIN colors and thinner print paste. THINNED print paste, add urea water as needed. Equal parts works well.

Warm water	1 cup (240 ml)
Granular urea	7 tsp (35 ml)



Step 4: Prepare dye concentrates.

Use warm water, <u>not over 95°F (35° C)</u>		
Warm water	1 cup (240 ml)	
Urea	2 Tbs to 4 Tbs (15 ml to 30 ml)	
Dye powder	2 Tbs (30 ml)	

Step 5: Prepare colors

Prepare colors by combining dye concentrate with print paste and/or urea water. Equal parts make a dark value.

Use less dye concentrate for lighter colors and more for very dark colors.

Step 6: Apply the colors

Apply to soda-soaked fabric. Use any surface design technique you choose

Step 7: Cure the dye.

Open or covered, flat or rolled, be sure to maintain a small amount of moisture.Time4 to 8 hoursTemperature70° F to 110° F (21° C to 43° C)MoistureAlmost dry to the touch or very wet

Step 8: Wash out excess dye.

Wash in warm water and Synthrapol. Final wash hot: 140° F (60° C).

Hand wash 1 tsp (5 ml)

Machine wash 1 Tbs to 4 Tbs (15 ml to 60 ml)

Test for wash fastness by ironing washed fabric (while it is still wet) on clean white cotton.